



ERS-100

P/N: 020-0006

For Professional Use Only



PRODUCT DESCRIPTION:

ERS-100 is an elastomeric, mineral-stabilized asphalt emulsion formulated with carefully selected raw materials for maximum performance and compatibility to deliver long-term service on the roof. It is manufactured using a state of the art colloid milling process to ensure a smooth, uniform consistency.

It is manufactured using a state of the art colloid milling process to ensure a smooth, uniform consistency.

RECOMMENDED USES:

ERS-100 can be used as a protective coating over smooth asphalt roofs, metal roofs and cured solvent borne primers and coatings. It can also be used with reinforcing fabrics over medium to severely alligatored asphalt flood coats and as dampproofing of masonry and concrete surfaces.

INSTALLATION: Ready to apply. Do not heat. Do not thin.

Surface Preparation: All work surfaces must be clean, damp or dry, but free of standing water, dirt, dust, debris, oils, loose and/or embedded gravel, unadhered coatings, deteriorated membranes, and other contaminants that may result in a surface that is not sound. All necessary repairs must be completed before application to ensure optimum performance. Extremely dusty or dry surfaces should be primed with Ecology ERS-301 Primer.

Application (reinforced): Apply to the properly prepared surface at a rate of 1-2 gallons per square. Embed the Ecology reinforcement (starter course), brushing the reinforcement into the coating. Assure that the reinforcement conforms to surface and no bridging or fish mouthing occurs. Apply another coat of adhesive. If desired, embed second course of reinforcement, overlapping the reinforcements. After the final reinforcement is applied, cover with the coating at a rate of 1-2 gallons per square.

Application (non-reinforced): Apply to the prepared surface at a rate of 2-3 gallons per square. To avoid pinholes and ensure maximum performance, application of two coats, each at 1/2 the total coverage rate and applied perpendicular to one another, are recommended.

Clean-Up: Immediately rinse/flush equipment and tools with mineral spirits after use, exercising all flammable liquid precautions. Use waterless hand cleaner on skin.

PACKAGING:

ERS-100 is available in 5-gallon pails (45 lbs.) and 55-gallon drums (507 lbs.).

PRECAUTIONS:

- **DO NOT** use with or on 100% rubber or plastic substrates.
- **DO NOT** use on or with products containing coal tar.
- **DO NOT** apply to areas that pond water.
- **DO NOT** apply if temperatures are expected to fall below 45°F (7.2°C) or rain or heavy dew is expected, within 24 hours of application.
- **DO NOT** use where this product may come in contact with potable water.
- **DO NOT THIN**
- **DO NOT FREEZE**

PHYSICAL PROPERTIES:

Property	Test Method	Result
Wt/gal, lbs.	ASTM D 6511	8.3 – 8.7
Solids, % by Weight	ASTM D 6511	48 – 52
% by Volume		48 – 52
Viscosity, cps	Brookfield, RVT	6500 – 10000
pH		6.2 – 7.2
Flash Point, °F	PMCC	None
Color, Cured	Visual	Black
Drying time, Touch	70°F/50% R.H.	1 – 2 hours
Shelf Life	70°F/50% R.H.	1 year
VOC	EPA Method 24A	zero

Ecology Roof Systems®

Corporate Offices

9821 Olde Eight Road, Unit F, Northfield, OH 44067

PHONE: 330-467-4220 FAX: 330-467-4225

www.ecologyroof.com

REGIONAL OFFICES LOCATED ACROSS THE U.S.

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. User must contact Ecology Roof Systems to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Ecology Roof Systems. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ECOLOGY ROOF SYSTEMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.