



PRODUCTS FOR OUR ENVIRONMENT

TECHNICAL DATA SHEET

ERS-303

P/N: 035-0165
For Professional Use Only



PRODUCT DESCRIPTION:

ERS-303 is a specially modified, trowel or gun applied mastic formulated with synthetic rubber, functional fillers, and solvents. ERS-303 quickly develops into a seamless rubber seal. Its unusual combination of high tensile strength and elongation and recovery make it the perfect cement to use in high stress areas. It will withstand rooftop movement and vibrations without splitting. This cement will withstand changing seasons and mechanical stresses as it forms a rubber-like seal that will form a waterproof seal for many years.

RECOMMENDED USES:

- Use for any rooftop repair, including: flashings, chimneys, cracks and splits, blisters or anywhere that a long lasting weatherproof seal is needed.
- Use where a superior roof cement is needed due to vibrations or high stress.

ADVANTAGES:

- Special rubber formulation increases elasticity and recovery.
- Can be used in high stress areas where regular roof cements will crack and fail.
- Will last longer than regular roof cements because of its rubber base and elasticity.
- Forms a rubber seal that will withstand mechanical stresses and form a weatherproof seal for years.

COVERAGE:

Coverage varies depending on the porosity and smoothness of the surface applied to. Between 4 to 8 gallons per 100 square feet can be expected.

INSTALLATION:

Surface Preparation: Remove all dirt, dust, debris and standing water by brooming or water pressure where necessary and where no danger or nuisance is caused to areas adjacent to work. All loose gravel must be removed from ballasted roofs. Scrape back to a hard edge all loose or scaled coating. Make sure surface edges of areas to be repaired are flush to surrounding surface. On metal roofs replace all loose or pushed-up fasteners with larger ones. Make sure all laps are tight. Rusted metal roofs or areas with scaled coating may require steel brushing and scraping.

Application: Apply by trowel to area to be repaired. Press material tightly into cracks, splits and seams in vertical and horizontal surfaces. To repair large cracks and splits, scrape or cut away rough open edges to make as flush as possible to surrounding surface. Apply a layer of ERS-303 to crack or split opening. Be sure to work material into opening; establishing a bond to all contact surfaces. Work material to a smooth, even surface and feather the edge to about two inches from sides and six inches from ends. For blisters, cut or scrape away the puffed up and debonded area. Allow to air dry, if moisture is present, and proceed with repair in the same way as for large cracks and splits.

Clean-up with mineral spirits, but do not thin the product with this or any other solvents.

For the easiest workability in cold temperatures, warm containers by storing them overnight in a room at 65° to 75°F.

Drying Time: Eight to twelve hours to a light touch. Heavy applications should not be subjected to foot traffic.

PACKAGING:

ERS-303 is available in cases of twelve 10.5 oz tubes.

PRECAUTIONS:

This product is combustible. Keep away from heat, sparks and open flame. Avoid repeated or prolonged contact with skin. If swallowed, do not induce vomiting. Contact Physician immediately. Keep container closed when not in use. **KEEP AWAY FROM CHILDREN.** Product label and MSDS contain further information on the safe use of this product and precautions for the safe disposal of the container. They should be read and understood prior to use.

RESTRICTIONS:

- Do not use with PVC film.
- Do not use where material, once applied, may come into contact with potable water.
- Not for use on or with products containing coal tar.
- Do not use on slate shingles or apply directly to wood surfaces.
- Surfaces to be repaired must be dry. Repaired areas must remain dry for 24 hours after application.
- Not for use over rubber or plastic membranes – asphalt modified only.
- For exterior use only

PHYSICAL PROPERTIES:

Property	Typical Value
Percent Solids by Weight	66%
Weight Per Gallon	9 lbs
Flash Point minimum	105°F (Seta C.C.)
Viscosity at 77°F	800,000 cps
Elongation at 77°F minimum	400%
Recovery from Elongation at 400%	90%
Recovery from Elongation at 100%	100%
Tensile Strength	600 psi
VOC	<500 g/l

Ecology Roof Systems®

Corporate Offices

9821 Olde Eight Road, Unit F, Northfield, OH 44067

PHONE: 330-467-4220 FAX: 330-467-4225

www.ecologyroof.com

REGIONAL OFFICES LOCATED ACROSS THE U.S.

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. User must contact Ecology Roof Systems to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Ecology Roof Systems. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ECOLOGY ROOF SYSTEMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.