



PRODUCTS FOR OUR ENVIRONMENT

TECHNICAL DATA SHEET

ERS-307-A

P/N: 020-0025 5 gal.
020-0026 55 gal.

For Professional Use Only



PRODUCT DESCRIPTION:

ERS-307-A is a balanced blend of premium oxidized asphalt and penetrating oils, further augmented with quality non-asbestos reinforcing fillers. ERS-307-A provides rejuvenating qualities to weathered asphalt BUR systems.

RECOMMENDED USES:

ERS-307-A rejuvenates aged asphalt flood coats, exposed and weathered roofing felts and fabrics.

ADVANTAGES:

- Cold applied by brush, squeegee or airless spray equipment.
- Eliminates the use of kettles and open flames.
- Rejuvenates aged asphalt flood coats and restores many of its original properties.
- Reseals cracks and other imperfections in the flood coat, extending the life of the roof system.
- Meets current Volatile Organic Compounds (VOC) regulations.
- Non-asbestos.

INSTALLATION: Ready to apply. Do not heat. Do not thin.

Surface Preparation: All work surfaces must be clean, dry, free of dirt, dust, debris, oils, loose and/or embedded gravel, unadhered coatings, deteriorated membranes, and other contaminants that may result in a surface that is not sound. All necessary repairs must be completed before application to ensure the optimum performance. All surfaces must be free of frost, snow and ice.

Application: Apply ERS-307-A at a rate of approximately 4 to 8 gallons per square, then re-embed gravel.

Clean-Up: Immediately rinse/flush equipment and tools with mineral spirits after use, exercising all flammable liquid precautions. Use waterless hand cleaner on skin.

STORAGE LIFE:

This product has a shelf life of 1 year at 70°F with 50% R.H.

PACKAGING:

ERS-307-A is available in 5 gallon pails (18.9 liters) (46 lbs) and 55 gallon drums (208.1 liters) (518 lbs).

PRECAUTIONS:

- **DO NOT** use with or on 100% rubber or plastic substrates.
- **DO NOT** use on or with products containing coal tar.
- **DO NOT** apply to damp or wet surfaces.
- **DO NOT** use where this product may come in contact with potable water.
- **DO NOT THIN.**

- EXTERIOR USE ONLY.

PHYSICAL PROPERTIES:

Property	Test Method	Result
Wt./gal, lbs.	ASTM D 6511	8.5 – 9.0
Solids, % by wt.	ASTM D 6511	75 – 80
% by vol.		70 – 75
Viscosity, grams	Stormer @ 200 rpm	700-1100
pH		N/A
Flash Point, °F	PMCC	105 min.
Color, cured	Visual	Black
Drying time, Touch	70°F with 50% R.H.	1 hours
Shelf Life	70°F with 50% R.H.	1 year
VOC	EPA Method 24A	300 gm/liter max.

Ecology Roof Systems®

Corporate Offices

9821 Olde Eight Road, Unit F, Northfield, OH 44067

PHONE: 330-467-4220 FAX: 330-467-4225

www.ecologyroof.com

REGIONAL OFFICES LOCATED ACROSS THE U.S.

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. User must contact Ecology Roof Systems to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Ecology Roof Systems. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ECOLOGY ROOF SYSTEMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.