



PRODUCTS FOR OUR ENVIRONMENT

TECHNICAL DATA SHEET

ERS-400-6 Ply Sheet

P/N: 045-0085

For Professional Use Only



PRODUCT DESCRIPTION:

ERS-400-6 Ply Sheet is manufactured with a heavyweight fiberglass mat containing heat-cured resinous binders. The high strength glass mat is saturated with TYPE VI asphalt, giving ERS-400-6 Ply Sheet excellent strength and weathering characteristics, as well as a uniform porosity for ease in application.

RECOMMENDED USES:

ERS-400-6 Ply Sheet is a ply sheet used in hot mopped roofing applications and may be the backbone reinforcement sheet used in all smooth and gravel surfaced built-up roofing systems requiring the ASTM D-2178 TYPE VI felt.

APPROVALS:



ADVANTAGES:

- Utilizes a roofing-dedicated asphalt to ensure premium roof system performance and durability.
- High quality, non-rotting ply sheet.
- Ease of handling – provides for a contractor friendly application.
- Contains no asbestos.
- Meets or exceeds the requirements of ASTM D 2178 for Type VI glass felts.
- Classified by Underwriters Laboratories Inc.® as to an external fire exposure only.
- Meets requirements of Factory Mutual Research Corporation® Standard 4470.

INSTALLATION:

Surface Preparation: In accordance with the particular job specifications, prepare surface to be covered.

Application: Plan placement of ERS-400-6 Ply Sheet to ensure that water will flow over or along, but not again exposed edges. Starting at low point of roof, apply uniform and continuous mopping of the specified hot-melt adhesive using a standard roofing mop or felt layer. To start and finish roof membrane along edges, termination and projections, use starting/finishing strips; 12", 24", and 36" wide plies with succeeding plies lapped 24-2/3" for 3-ply membrane. Four ply membranes can also be constructed by installing starter strips of 9", 18", 27" then 36", with succeeding plies overlapping 27-1/2".

Embed each ply in uniform and continuous mopping of specified hot-melt adhesive. Ply shall never touch ply. Apply specified hot-melt adhesive no more than ten feet ahead of each roll (less in cool weather). Lightly broom plies from unmapped side to ensure complete adhesion. Overlap previous day's work by 24". Lap ply sheet ends 6". Stagger end laps 4' minimum or when lap ends are in line, cover with two (2) plies of full width ERS-400-6 Ply Sheet. Avoid walking on plies until adhesive has cooled. Install flashings as specified.

PACKAGING:

5 Sq. roll – 36" wide x 180' long; 20 rolls per pallet.

STORAGE:

One (1) year from date of shipment when stored in a cool, dry place, preferably indoors.

PHYSICAL PROPERTIES:

Property	Typical Value	Test Method
Breaking Strength	77 lbf/in MD 72 lbf/in XMD	ASTM D 2178
Pliability	Pass	ASTM D 2178
Ash	70 – 88%	ASTM D 2178
Bituminous Saturant	7.6 lb/100ft ² (1)	ASTM D 2178
Mass of Desaturated Felt	1.9 – 2.2 lb/100ft ²	ASTM D 2178
Asbestos Content	0%	EPA 600/R-93/116
Fire Resistance	Pass	ASTM E 108 / UL 790
Adherent Comminuted Surfacing	3.0 lb/100ft ² , max.	ASTM D 2178
Dry Mass of Asphalt-Impregnated Glass Felt	6 lb/100ft ² , min.	ASTM D 2178
Compatibility of Felt Coating with Asphalt Roofing Bitumen	Oliensis Test, No Exudate	ASTM D 1370
Actual test result versus ASTM minimum		

Ecology Roof Systems®

Corporate Offices

9821 Olde Eight Road, Unit F, Northfield, OH 44067

PHONE: 330-467-4220 FAX: 330-467-4225

www.ecologyroof.com

REGIONAL OFFICES LOCATED ACROSS THE U.S.

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. User must contact Ecology Roof Systems to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Ecology Roof Systems. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ECOLOGY ROOF SYSTEMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.