



PRODUCTS FOR OUR ENVIRONMENT

TECHNICAL DATA SHEET

ERS-584 GR FR H

P/N: 045-0155

For Professional Use Only



PRODUCT DESCRIPTION:

ERS-584 GR FR H is 132 mils (3.3 mm) thick and is composed of selected SBS modified bitumen applied onto a fiberglass/non-woven polyester composite reinforcement and is produced with plastic underside and granules topside. ERS-584 GR FR H is adhered to a sand surfaced base membrane by using hot asphalt or cold adhesive. ERS-584 GR FR H is tested in accordance with ASTM D 5147.

RECOMMENDED USES:

ERS-584 GR FR H can be used as part of a high performance SBS modified bitumen roof system utilizing torch welding methods. It can also be used as a flashing membrane for new construction and remedial or maintenance applications.

ADVANTAGES:

- Weather resistant for long-term performance.
- Excellent cold weather performance.
- Contains no asbestos.
- Uniform layer of protection provided by quality control during manufacture.
- Meets or exceeds ASTM D 5147.
- Meets requirements of Factory Mutual Research Corporation® Standard 4470.
- Classified by Underwriters Laboratories, Inc.® as to an external fire exposure.

APPROVALS:



INSTALLATION: Caution – if your torch experience has been with APP membranes only, be advised that torch grade (TG) SBS membranes require less heat to reach proper application temperature. Practice on scrap membrane before installing.

Surface Preparation: The surface over which the sheet is to be installed must be firm, dry, smooth and compatible with the membrane and application method and free of debris and loose material. All surfaces must be designed and installed in accordance with specifications. Positive drainage is required.

Application: Apply ERS-301 (asphalt primer) to all metal, concrete, and other porous surfaces and allow to dry prior to installation of the roofing membrane and flashing. **Never weld directly to combustible materials.**

Roofing shall commence at the lowest point of the roof (running rolls perpendicular to the slope) with laps installed so that water flows over, rather than against, the lap. On inclines exceeding 1" per foot, the membrane may be installed with side laps running parallel to the direction of the roof slope (strapping method).

Side laps shall be 3" and end laps a minimum of 6". End laps must be staggered a minimum of 3'.

COVERAGE:

Lapping width determines actual coverage of roll – i.e., 3" side and 6" end laps provide approximate coverage of .975 squares.

PACKAGING:

ERS-584 GR FR H comes in a 39" x 33' roll; 25 rolls per pallet.

STORAGE:

One (1) year from date of shipment when stored in a cool, dry place, preferably indoors.

PRECAUTIONS:

- If your torch experience has been with APP membranes only, be advised that torch grade SBS membranes require **less heat to reach proper application temperature.**
- Protect all components of Ecology's assemblies from discharges such as petroleum products, grease, oil (petroleum and vegetable) and constant contact with water in excess of 140°F (60°C).
- Do not apply directly to previously coated surfaces or existing mineral surface roofs. The use of a mechanically attached insulation or base sheet separator is required.
- When ambient temperatures are below 50°F (10°C), material should be kept in a warm area (60°F (15.6°C) or higher) and brought to the roof no more than one hour prior to the application.
- Do not apply directly to the following surfaces unless they are primed with ERS-301 (asphalt primer): Gypsum, Stucco, Textured Masonry, any Metal.
- Copper flanges may be weathered or coated with an anti-tarnish lacquer, which impair adhesion. Clean with acetone and clean rags. Prime with ERS-301 (asphalt primer) before applying flashing membrane.
- Do not use mastic behind Ecology's torch grade membranes.

PHYSICAL PROPERTIES: (Typical Value)

Physical Property per ASTM D 5147	MD	XD
Tensile – Max Load at 0 ± 3.6°F lbf/in	72	50
Elongation at 0 ± 3.6°F %	33	42
Tensile – Max Load at 73.4 ± 3.6°F lbf/in	49	44
Elongation at 73.4 ± 3.6°F %	39	41
Tear Strength at 73.4 ± 3.6°F lbf	102	71
Low Temperature Flex °F max	-15	-15
Dimensional Stability % max	<0.5	<0.5
Compound Stability Temp °F	215	215
Granule Embedment g/max	<2	<2

Minimum values before and after heat conditioning.

Ecology Roof Systems®

Corporate Offices

9821 Olde Eight Road, Unit F, Northfield, OH 44067

PHONE: 330-467-4220 FAX: 330-467-4225

www.ecologyroof.com

REGIONAL OFFICES LOCATED ACROSS THE U.S.

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. User must contact Ecology Roof Systems to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Ecology Roof Systems. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ECOLOGY ROOF SYSTEMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.